

HIGH PERFORMANCE SCREEN FABRIC
FOR DOMESTIC & CONTRACT MARKET



RAY-SCREEN®

300
PURE
3%

Composition	75% PVC - 25 % Polyester
Weight	± 300 g/m ²
Thickness	± 0,40 mm
Width	300 cm
Fire Classification	M1 - B1
Health & Safety	Greenguard - Oeko-Tex®
Tensile strength (warp)	125 daN/5cm
Tearing strength (warp)	>2 daN
Tensile strength (weft)	120 daN/5cm
Tearing strength (weft)	>2 daN
Colour Fastness	7 (ISO 105 B02)
Microorganisms	ISO 846



Colour	T _s	R _s	A _s	T _{uv}	T _v	OF	Interior		
							g _{tot}	Fc	Class
col01	22	67	11	6	17	3	0,35	0,59	2
col03	15	47	38	4	10	3	0,40	0,68	1
col05	3	12	85	2	2	3	0,49	0,84	1
col18	3	21	76	2	2	3	0,47	0,79	1

Ts Solar Transmittance - Rs Solar Reflectance - As Solar Absorptance - Tuv UV Transmittance - Tv Visible Light Transmittance
OF Openness Factor

Measurements according to EN410, Glass Type C
Classification according to EN14501

