

HIGH PERFORMANCE SCREEN FABRIC
FOR DOMESTIC & CONTRACT MARKET



RAY-SCREEN[®]

420
COMBI
10%

Composition	75% PVC - 25 % Polyester
Weight	± 390 g/m ²
Thickness	± 0,50 mm
Width	300 cm
Fire Classification	M1 - B1
Health & Safety	Greenguard - Oeko-Tex [®]
Tensile strength (warp)	165 daN/5cm
Tearing strength (warp)	>7 daN
Tensile strength (weft)	155 daN/5cm
Tearing strength (weft)	>6 daN
Colour Fastness	7 (ISO 105 B02)
Microorganisms	ISO 846



Colour	T _s	R _s	A _s	T _{UV}	T _v	OF
col01	25	63	12	10	20	10
col03	19	45	36	11	15	10
col05	9	4	87	9	9	10

Interior		
g _{tot}	Fc	Class
0,36	0,62	1
0,41	0,70	1
0,52	0,88	0

Ts Solar Transmittance - Rs Solar Reflectance - As Solar Absorptance - Tuv UV Transmittance - Tv Visible Light Transmittance
OF Openness Factor

Measurements according to EN410, Glass Type C
Classification according to EN14501

