

HIGH PERFORMANCE SCREEN FABRIC
FOR DOMESTIC & CONTRACT MARKET



RAY-SCREEN[®]

425
CONTRA
3%

Composition	75% PVC - 25 % Polyester
Weight	± 425 g/m ²
Thickness	± 0,60 mm
Width	300 cm
Fire Classification	M1 - B1
Health & Safety	Greenguard - Oeko-Tex [®]
Tensile strength (warp)	160 daN/5cm
Tearing strength (warp)	>12 daN
Tensile strength (weft)	170 daN/5cm
Tearing strength (weft)	>19 daN
Colour Fastness	7 (ISO 105 B02)
Microorganisms	ISO 846



Colour	T _s	R _s	A _s	T _{uv}	T _v	OF
col01	20	64	16	3	14	3
col03	21	43	36	6	17	3
col04	13	24	63	5	9	3
col05	6	10	84	4	6	3

Interior		
g _{tot}	Fc	Class
0,36	0,61	1
0,42	0,71	1
0,47	0,79	1
0,50	0,85	0

Ts Solar Transmittance - Rs Solar Reflectance - As Solar Absorptance - Tuv UV Transmittance - Tv Visible Light Transmittance
OF Openness Factor

Measurements according to EN410, Glass Type C
Classification according to EN14501

